

DULUX[®] AUTOSPEED[®]

488 89287 2K HS PRIMER FILLER



Dulux Australia
ABN 67 000 049 427

488 89287 Dulux AUTOSPEED[®] 2K HS Primer

Product Name:

488-89287 Dulux[®] AutoSpeed[®] 2K HS Primer

Product Description:

Dulux[®] AutoSpeed[®] 2K HS Primer is a premium quality two pack High Solids polyurethane primer that can be used as a filler or surfacer in auto refinishing. It provides excellent build and excellent hold out.

Substrates

Suitably prepared:

- Existing finishes
- Polyester Filler
- Bare steel surfaces
- OEM Primer
- Fibreglass

Product & Additives:








Dulux[®] AutoSpeed[®] 2K HS Primer 488-89287

Dulux[®] AutoSpeed[®] 2K 4:1 Hardener- Normal 980-89291

Dulux[®] AutoSpeed[®] RP 4:1 Hardener- Fast 980-89794 Cold Temperatures/ Rapid Production

Dulux[®] AutoSpeed[®] 2K Thinner- Normal 920-89292

Dulux[®] AutoSpeed[®] RP Thinner - Fast 920-89819 Cold Temperatures/ Rapid Production








	Mixing Ratio	4 Part 488-89287
	Hardener	1 Part 980-89291 Large Areas or 1 Part 980- 89794 Small Areas
	Thinner	Filler 5-10% 920-89292 or 920-89819 2 to 3 coats Max Surfacer 15-20% 920-89292 or 920-89819 2 to 3 coats Max
	Spray Viscosity DIN Cup 4 @ 25°C	22 - 24 seconds
	Gravity Feed	Fluid Tip: CONVENTIONAL: 1.5 - 1.8mm HVLP: 1.5 - 1.9mm Spraying Pressure: 340 kPa. 70 kPa. Or refer to manufacturer's recommendations
	Suction Feed	CONVENTIONAL: 1.7 - 2.0mm HVLP Gravity Feed: 1.8 - 2.2mm 340 kPa. 70 kPa. Or refer to manufacturer's recommendations
	Air Flash	5 - 10 minutes air flash between coats

DULUX[®] AUTOSPEED[®] 488 89287 2K HS PRIMER FILLER



Dulux Australia
ABN 67 000 049 427

488 89287 Dulux AUTOSPEED[®] 2K HS Primer

	Baking/Drying	3 hours @ 20°C 30 mins @ 60°C
	Infrared	Short wave: 8 mins Medium wave: 10 - 15 mins
	Sanding - Manual	Wet: P600 - P800 Grit
	Sanding - Manual	Dry: P400 - P600 Grit
	Sanding - Mechanical	Dry: P400 - P600 Grit
	Spraying	Use air fed mask at all times. Refer applicable AS/NZS Standards
	Pot Life	When mixed, 45 minutes @ 20°C
	Application	Filler 2 to 3 coats Surfacer 2 coats

DULUX® AUTOSPEED®

488 89287 2K HS PRIMER FILLER



Dulux Australia
ABN 67 000 049 427

488 89287 Dulux AUTOSPEED® 2K HS Primer

Weight Mixing Ratios for 488-89287 Autospeed 2K Primer and Flex 485-89930

a. Using the Intelligent balance and adding by percentage addition

Note: This order of addition must be maintained when using the intelligent balance. The RFU volume is approx 50% larger than the initial volume of primer.

488-89287 Autospeed primer	100
485-89930 Flex Additive	7.3%
980-89291 2K Primer Hardener	23.8%
920-89292 2K Thinner	5.4%

The quantity of thinner added can be varied to suit your spraying conditions. See notes below regarding alternate thinners and hardener.

b. Using an ordinary balance and adding by grams.

Volume of RFU Primer (ml)	488-89287 Primer (g)	485-89930 Flex (g)	980-89291 Hardener* (g)	920-89292 Thinner ** (g)
50	47.89	3.50	12.22	3.34
100	95.78	7.0	24.43	6.79
150	143.7	10.5	36.65	10.18
200	191.6	14.0	48.86	13.58
250	239.5	17.5	61.07	16.98
300	287.3	21.0	73.29	20.37
350	335.2	24.5	85.50	23.77
400	383.1	28.0	97.72	27.16
450	431.0	31.5	109.9	30.56
500	478.9	35.0	122.15	33.95
550	526.8	38.5	134.4	37.35
600	574.7	42.0	146.6	40.74
650	622.6	45.5	158.8	44.14
700	670.5	49.0	171.0	47.53
750	718.4	52.5	183.2	50.93
800	766.2	56.0	195.4	54.32
850	814.1	59.5	207.7	57.72
900	862.0	63.0	219.9	61.11
950	909.9	66.5	232.1	64.50
1000 (1L)	957.8	70	244.3	67.9

* Use 980-89294 Autospeed RP 2K Primer Hardener for improved production times

** Use 920-89819 Autospeed RP Thinner in cold weather or 920-89847 Autospeed Hot Weather Thinner as required.

DULUX[®] AUTOSPEED[®]

488 89287 2K HS PRIMER FILLER



Dulux Australia
ABN 67 000 049 427

Weight Mixing Ratios for 488-89287 Autospeed 2K Primer

b. Using the Intelligent balance and adding by percentage addition

Note: This order of addition must be maintained when using the intelligent balance. The RFU volume is approx 50% larger than the initial volume of primer.

488-89287 Autospeed primer	100
980-89291 2K Primer Hardener	15.8%
920-89292 2K Thinner	15.8-31.5%

The quantity of thinner added can be varied to suit your spraying conditions. See notes below regarding alternate thinners and hardener.

c. Using an ordinary balance and adding by grams 10% Thinner.

Volume of RFU Primer (ml)	488-89287 Primer (g)	980-89291 Hardener* (g)	920-89292 Thinner ** (g)
50	57.70	9.10	3.32
100	115.41	18.20	6.64
150	173.11	27.31	9.97
200	230.82	36.41	13.29
250	288.52	45.52	16.62
300	346.23	54.62	19.94
350	403.93	63.73	23.27
400	461.64	72.83	26.59
450	519.34	81.94	29.92
500	577.05	91.04	33.24
550	634.75	100.15	36.57
600	692.46	109.25	39.89
650	750.16	118.36	43.22
700	807.87	127.46	46.54
750	865.57	136.57	49.87
800	923.28	145.67	53.19
850	980.98	154.78	56.52
900	1038.69	163.88	59.84
950	1096.39	172.99	63.17
1000 (1L)	1154.10	182.09	66.49

* Use 980-89294 Autospeed RP 2K Primer Hardener for improved production times

** Use 920-89819 Autospeed RP Thinner in cold weather or 920-89847 Autospeed Hot Weather Thinner as required.

DULUX® AUTOSPEED® 488 89287 2K HS PRIMER FILLER



Dulux Australia
ABN 67 000 049 427

d. Using an ordinary balance and adding by grams 20% Thinner.

Volume of RFU Primer (ml)	488-89287 Primer (g)	980-89291 Hardener* (g)	920-89292 Thinner ** (g)
50	53.72	8.47	6.19
100	107.43	16.95	12.38
150	161.15	25.42	18.57
200	214.87	33.90	24.76
250	268.59	42.38	30.95
300	322.30	50.85	37.14
350	376.02	59.33	43.33
400	429.74	67.80	49.52
450	483.45	76.28	55.71
500	537.17	84.76	61.90
550	590.89	93.23	68.09
600	644.60	101.71	74.28
650	698.32	110.18	80.47
700	752.04	118.66	86.66
750	805.76	127.14	92.85
800	859.47	135.61	99.04
850	913.19	144.09	105.23
900	966.91	152.56	111.42
950	1020.62	161.04	117.61
1000 (1L)	1074.34	169.52	123.80

* Use 980-89294 Autospeed RP 2K Primer Hardener for improved production times

** Use 920-89819 Autospeed RP Thinner in cold weather or 920-89847 Autospeed Hot Weather Thinner as required.

DULUX[®] AUTOSPEED[®] 488 89287 2K HS PRIMER FILLER



Dulux Australia
ABN 67 000 049 427

For Safe Handling:

Please refer to the Material Safety Data Sheet number: 462 for this product before use.

In the event of an emergency contact: 1 800 033 111 (ALL HOURS), NZ 0800 734 607

For further information contact:

Dulux Australia

1956 Dandenong Rd, Clayton,
Victoria, 3168

Australia

ABN 67 000 049 427

Telephone:

1 800 810 114

Fax:

61 3 9314 0596

Dulux New Zealand

31B Hillside Road

Glenfield, Auckland
New Zealand

Telephone:

0800 800 424

488 89287 Dulux AUTOSPEED[®] 2K HS Primer

Dulux and Autospeed are registered trademarks. Marks followed by the symbol [™] are trademarks.

DISCLAIMER: Any advice, recommendation, information, assistance or service provided by Dulux Refinish Coatings in relation to goods manufactured by it or their use and application is given in good faith and is believed by Dulux Refinish Coatings to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by Dulux Refinish Coatings provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon Dulux Refinish Coatings by any condition or warranty implied by applicable legislation, regulation or other Government ordinance voiding or prohibiting such exclusion, limitation or modification