

# DULUX® AUTOSPEED® 485 89913 PT Universal Blender



Dulux Australia  
ABN 67 000 049 427

485 89913 Dulux® Autospeed® PT Universal Blender

## Product Name:







485-89913 Dulux® Autospeed® PT Universal Blender

## Product Description:

Dulux® Autospeed® PT Universal Blender is a one of a range of premium products developed for automotive refinishing. When used in conjunction with Autospeed® 485-89918 PT Blending Clear, a consistent, even blend out of colours can be achieved. It is a valuable tool in achieving the required finish in the Dulux® Autospeed® colour range and Dulux® Autospeed® clear coat range.

## Product & Additives:

Dulux® Autospeed® PT Blending Clear 485-89918  
 Dulux® Autospeed® Standard Thinner 920-89909  
 Dulux® Autospeed® Low Temp Thinner 920-89908 (Small areas & Colder Temperatures)  
 Dulux® Autospeed® High Temp Thinner 920-89910 (High Temperatures)

|   |                     |  |
|---|---------------------|--|
|  | <b>Mixing Ratio</b> | 10-20% by weight PT Blending Clear 485-89918<br><br>80-90% by weight Universal Blender 485-89913   |
|  | <b>Gravity Feed</b> | <b>Fluid Tip:</b><br>CONVENTIONAL: 1.2 - 1.5mm<br>HVLP: 1.5 - 1.9mm<br><br><b>Spraying Pressure:</b><br>400 kPa/4 bar<br>70 kPa/0.7 bar<br><small>Or refer to manufacturer's recommendations</small> |
|  | <b>Suction Feed</b> | CONVENTIONAL: 1.4 - 1.8mm<br>HVLP: 1.8 - 2.0mm<br><br>400 kPa/4 bar<br>70 kPa/0.7 bar<br><small>Or refer to manufacturer's recommendations</small>   |
|  | <b>Application</b>  | Single wet coats applied thinly, avoiding primed area.   |
|  | <b>Air Flash</b>    | 3 - 5 minutes air flash  |
|  | <b>Spraying</b>     | Use air fed mask at all times.<br>Refer applicable AS/NZS Standards  |

# DULUX® AUTOSPEED®

**485 89913 PT Universal Blender**



Dulux Australia  
ABN 67 000 049 427

## For Safe Handling:

Please refer to the Material Safety Data Sheet No: 21696 for this product before use. This product may contain materials that are being introduced to Australia under a permit.

**In the event of an emergency contact: 1 800 033 111 (ALL HOURS)**

## For further information contact:

Dulux Australia  
1956 Princes Hwy, Clayton, Victoria, 3168  
Australia  
ABN 67 000 049 427  
Telephone: 1 800 810 114  
Fax: 61 3 9314 0596

**Telephone:**

**Fax:**

Dulux and Autospeed are registered trademarks. Marks followed by the symbol ™ are trademarks.

DISCLAIMER: Any advice, recommendation, information, assistance or service provided by Dulux Refinish Coatings in relation to goods manufactured by it or their use and application is given in good faith and is believed by Dulux Refinish Coatings to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by Dulux Refinish Coatings provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon Dulux Refinish Coatings by any condition or warranty implied by applicable legislation, regulation or other Government ordinance voiding or prohibiting such exclusion, limitation or modification